

Prüfbericht - Nr.: <i>Test Report No.:</i>	IND/BLR/CH/2018/1501R	Seite 1 von 3 <i>Page 1 of 3</i>	
Auftraggeber: <i>Client:</i>	Sunflex Recycling Pvt Ltd Plot No. – 274/4, Shital Estate B/H Satyamev Complex, Opp. Gujrat High Court, S. G. Highway, Sola Ahmedabad, 380060, India		
Gegenstand der Prüfung: <i>Test item:</i>	Rubber Tiles		
Bezeichnung: <i>Identification:</i>	Serien-Nr.: <i>Serial No./ Document Submitted:</i>		
Wareneingangs-Nr.: <i>Receipt No.:</i>	06032018	Eingangsdatum: <i>Date of receipt:</i>	06.03.2018
Order No.:	1803301976	Testing Period:	15.03.2018 to 16.03.2018
Prüfart: <i>Testing location:</i>	TÜV Rheinland India Pvt Ltd, Plot No. 27/B, 2nd Cross Road, Electronics City , Phase 1, Bangalore - 560 100, Karnataka, India.		
Prüfgrundlage: <i>Test specification:</i>	Customer's Requirement : Compression Deflection Test as per DIN 53577		
Prüfergebnis: <i>Test Result:</i>	Refer Page No.2 to 3		
Prüflaboratorium/ Testing Laboratory:			
zusammengestellt/ compiled by:		kontrolliert/ checked by:	
17.03.2018	Ranabir Pal Manager - Polymer Section, Material Testing Laboratories, Industry Services	17.03.2018	Rajesh Jain B Technical Head, Material Testing Laboratories, Industry Services
Datum <i>Date</i>	Name <i>Name</i>	Unterschrift <i>Signature</i>	Datum <i>Date</i>
			Name <i>Name</i>
			Unterschrift <i>Signature</i>
Sonstiges/ Other Aspects: Report has been revised to update sample name as requested by client			
Abkürzungen:	ok / P = entspricht Prüfgrundlage fail / F = entspricht nicht Prüfgrundlage n.a. / N = nicht anwendbar	Abbreviations:	ok / P = passed fail / F = failed n.a. / N = not applicable
Dieser Prüfbericht bezieht sich nur auf das o.g. Prüfmuster und darf ohne Genehmigung der Prüfstelle nicht auszugsweise vervielfältigt werden. Dieser Bericht berechtigt nicht zur Verwendung eines Prüfzeichens. <i>This test report relates to the a. M. Test sample. Without permission of the test center this test report is not permitted to be duplicated in extracts. This test report does not entitle to carry any safety mark on this or similar products. Test item submitted by client. Sampling not done by TUVRI</i>			

Prüfbericht - Nr.:
Test Report No.:

IND/BLR/CH/2018/1501R

Seite 2 von 3
Page 2 of 3

TEST RESULTS




Sample Photograph as in Received Condition

Test Name: Compression Deflection Test

Test Method: DIN 53577

Test Condition: Lab Environmental condition - $23\pm 2^{\circ}\text{C}$, $50\pm 5\% \text{RH}$
Test Speed – 5 mm/min.
Pre – Load – 2 N



Photograph of Test Setup during test

Prüfbericht - Nr.:
Test Report No.:


IND/BLR/CH/2018/1501R

Seite 3 von 3
Page 3 of 3

Observations:

Sr. No.	Width (mm)	Thickness (mm)	Strain @50N (%)	Strain @100N (%)
1	100	42.5	0.66	0.86
2	100	42.5	0.74	0.98
3	100	42.5	0.74	0.95
Average			0.71	0.93

Stress vs. Strain Graph:



---- End of Report ----